

**Quality: GRAVURA**

**Collektion: Ulf Moritz by Vorwerk**

**Description of good:** woven, loop/velours  
**Coating:** jute/polypropylene

**Pile utility coat:** 100 % new wool



**strain value**



**comfort value**

Partition / 10 cm	ca.	35	Pile inset weight g/m <sup>2</sup>	ca.	980
Prick rate / 10 cm	ca.	17	Total weight g/m <sup>2</sup>	ca.	1630
Nap rate in dm <sup>2</sup>	ca.	595	Pile utility coat weight g/m <sup>2</sup>	ca.	660
Pile thickness in mm	ca.	6,3	Pile raw density g/cm <sup>3</sup>	ca.	0,106
Total thickness in mm	ca.	8,4			

**Confalgrative behavior**      **DIN EN 13501-1**      E<sub>fl</sub>

<b>Resistance to water</b>	DIN EN ISO 105-E 01 Change of colour	mind. Note 4
<b>Resistance to light</b>	DIN EN ISO 105-B 02	mind. Note 5
<b>Resistance to friction</b>	DIN EN ISO 105-X 12	mind. Note 4

In order to avoid change or measure, we recommend a fixed laying (glue with dispersion adhesive). Laying manual: see current maintenance and laying manual. Because of permanent further development and improvement of quality any change of technical data is reserved.