


Quality:	LYRICA	Collection:	Fascination
Construction:	1/10" soft-gloss-saxony	Pile material:	100% polyamide
Backing:	Texback®super	Carrier material:	PES-Fleece



Gauge / 10 cm	ca.	39,5	Pile inset weight g/m ²	ca.	1260
Tufts / 10 cm	ca.	41	Primary backing weight g/m ²	ca.	120
Points dm ²	ca.	1620	Total weight g/m ²	ca.	2100
Pile thickness mm	ca.	8,0	Weight of backing g/m ²	ca.	825
Total thickness mm	ca.	11,0	Weight of pile material g/m ²	ca.	1020
			Pile density g/cm ³	ca.	0,128

Castor chair test	DIN EN 985	r > 2,0							
Sound impact	DIN EN ISO 717-2	glued Δ Lw	27 dB						
Sound absorbtion	DIN EN ISO 354	Hz	125	250	500	1.000	2.000	4.000	
	verklebt	αs	0,03	0,04	0,14	0,38	0,70	0,91	
Heat flux	DIN ISO 8302: 1991	1/λ =	0,08	m ² K/W					
Fire rating	DIN EN 13501-1	E _{fl}							

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes	N. 4		
Fastness to light	DIN EN ISO 105-B 02	N. 5		
Fastness to rubbing	DIN EN ISO 105-X 12	N. 4		

This good is applicable for laying on floors with floor heatings when adhesion covers all the surface and dispersion adhesive was used which is resisting heat and deterioration. This quality is suitable for the following types of fitting: tackifier adhesive, dispersion adhesive, Ecofix (full area adhesion). Kindly contact us for advise on suitable non-woven-bonding underlays and stretching on needlebars. (Please refer to our current laying instructions.) Because of permanent further development and improvement of quality change of technical data is reserved.