

Quality:	NERZ	Collection:	Fascination
Construction:	1/16" tufted velours, plain	Pile material:	100% polyamide
Backing:	Texback®super	Carrier material:	PES-Fleece



1658-CPD-1017
Vorwerk & Co. Teppichwerke GmbH & Co. KG
Kuhlmannstrasse 11
D - 31785 Hameln
EN 14041: 2004

EN 1307



Gauge / 10 cm	ca.	63	Pileinset weight g/m ²	ca.	750
Tufts / 10 cm	ca.	110	Primary backing weight g/m ²	ca.	130
Points dm ²	ca.	6930	Total weight g/m ²	ca.	1700
Pile thickness mm	ca.	5,0	Weight of backing g/m ²	ca.	700
Total thickness mm	ca.	8,0	Weight of pile material g/m ²	ca.	600
			Pile density g/cm ³	ca.	0,120

Castor chair test	DIN EN 985	r ≥ 2,0	
Sound impact	DIN EN ISO 717-2	Δ Lw	27 dB
Sound absorbtion	DIN EN ISO 354	Hz	125 250 500 1.000 2.000 4.000
		αs	0,01 0,03 0,14 0,39 0,64 0,69
Heat flux	DIN ISO 8302: 1991	1/λ =	0,11 m² K/W
			Suitable for glueing on hot water-underfloor heating systems.
Fire rating	DIN EN 13501-1		C_{fl} -S1 not glued, glued or burred

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This article is suitable for fitting on subfloors with hotwater underfloor heating if glued on the full area with heat ageing resistant dispersion glue. To avoid dimensional change, we recommend firm fitting (glueing with dispersion glue or fitting with the VORWERK Ecofix® hook and loop system. Fitting recommendation: please refer to the current maintenance- and fitting recommendation. In the course of constant further development and product improvement we reserve the right to adapt our technical details accordingly.