


Quality:	ODINA	Collection:	Fascination
Construction:	1/10" tufted saxony, multi-coloured	Pile material:	100 % polyamide
Backing:	Texback® super	Carrier mterialt:	PES-Fleece



Gauge / 10 cm	ca.	39,5	Pile inset weight g/m ²	ca.	1200
Tufts / 10 cm	ca.	29	Primary backing weight g/m ²	ca.	120
Points dm ²	ca.	1131	Total weight g/m ²	ca.	2070
Pile thickness mm	ca.	6,7	Weight of pile material g/m ²	ca.	840
Total thickness mm	ca.	10,0	Pile density g/cm ³	ca.	0,125

Castor chair test	DIN EN 985	r ≥ ---	
Sound impact	DIN EN ISO 717-2	Δ Lw	29 dB
Sound absorbtion	DIN EN ISO 354	Hz	125 250 500 1.000 2.000 4.000
		αs	0,01 0,05 0,15 0,32 0,63 0,85
Heat flux	DIN ISO 8302: 1991	1/λ =	0,15 m ² K/W
Fire rating	DIN EN 13501-1	E _{fl}	

Static resistance	DIN EN 1815 Bl. 2	< 2,0	KV	b. 25% rel. F.
Surface resistance	DIN ISO/DIS 10965 Bl. 1 R _{OT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Vertical resistance	DIN ISO/DIS 10965 Bl. 1 R _{DT}	< 10 ¹⁰	Ω	b. 25% rel. F.
Fastness to water	DIN EN ISO 105-E 01 Colour-changes		N. 4	
Fastness to light	DIN EN ISO 105-B 02		N. 5	
Fastness to rubbing	DIN EN ISO 105-X 12		N. 4	

This article is suitable for fitting on subfloors with hotwater underfloor heating if glued on the full area with heat ageing resistant dispersion glue. To avoid dimensional change, we recommend firm fitting (glueing with dispersion glue or fitting with the VORWERK Ecofix® hook and loop system.) Fitting recommendation: please refer to the current maintenance- and fitting recommendation. In the course of constant further development and product improvement we reserve the right to adapt our technical details accordingly.