

Quality: OPALIA

Collektion: Ulf Moritz by Vorwerk

Description of good: woven, loop/elours
Coating: jute

Pile utility coat: 100 % new wool





**Vorwerk & Co. Teppichwerke
GmbH & Co. KG
Kuhlmannstrasse 11
D – 31785 Hameln**

EN 14041: 2004




EN 1307



strain value



comfort value

Partition / 10 cm	ca.	15,7	Pile inset weight g/m²	ca.	--
Prick rate / 10 cm	ca.	28	Total weight g/m²	ca.	3150
Nap rate in dm²	ca.	440	Pile utility coat weight g/m²	ca.	1350
Pile thickness in mm	ca.	7,7	Pile raw density g/cm³	ca.	0,170
Total thickness in mm	ca.	11,0			

Confalgrative behavior **DIN EN 13501-1** E_{fl}

Resistance to water DIN EN ISO 105-E 01 Change of colour mind. Note 4
Resistance to light DIN EN ISO 105-B 02 mind. Note 5
Resistance to friction DIN EN ISO 105-X 12 mind. Note 4

In order to avoid change or measure, we recommend a fixed laying (glue with dispersion adhesive). Laying manual: see current maintenance and laying manual. Because of permanent further development and improvement of quality any change of technical data is reserved.