

LOCARNO:

Style Number

LRN

Specifications

Construction	Textured Loop Pattern
Yarn Content	BOLYU® SD Nylon / BCF
Dye Method	Solution / Space
Machine Gauge	1/10 in. (39.4 col./10 cm.)
Stitch Count	13 S.P.I. (51.2/10 cm.)
Finished Pile Thickness	.144 in. (3.66 mm.)
Average Density	7,500
Yarn Weight Tufted	30 oz./yd.2 (1017 g./m2)
Primary Backing	Masterline® Woven Primary
Secondary Backing	Woven Polypropylene with Post Consumer Recycled Content
Width	12 feet (3.66m.)
Pattern Repeat	.80" w x .46" l (2.0 cm. x 1.8 cm.)
Total Recycled Content	2.43%

Performance

Static Control	Less Than 3.5 k.v. Step
Flame Resistance	Passes (DOC FF-1-70)
Flooring Radiant Panel	Class 1 (ASTM E-648)
Smoke Density	Less Than 450 (ASTM E-662)
Soil Resistance	Commercial Anti-Soil Protection
CRI Green Label Plus	Certification #GLP7078

Warranties

Wear	10 Year Limited Warranty
Static	Lifetime Warranty
Stain	Lifetime Limited Warranty

Additional Information

Custom Colors	Contact Sales Representative
Backing Options	See iLoc® backings at www.bolyu.com
Coordinating Styles	Multiple
Samples	800 451 1250

Specifications are based on averages from manufacturing processes and may vary within normal industry tolerances. Components may be changed without notice due to raw material shortages and/or technological advances. Such variances do not affect performance.



BOLYU

201 Princeton Boulevard
Adairsville, Georgia 30103
800 451 1250

335 Roxton Street
Acton Vale, Quebec
Canada J0H 1A0
888 467 5075

A Beaulieu Commercial Brand