SPECIFICATIONS

Construction Textured Loop

Yarn Content Cambridge Approved Nylon

Dye Method Solution

 Machine Gauge
 1/10 in. (39.4 col./10 cm.)

 Stitch Count
 9.3 S.P.I. (36.7/10 cm.)

Finished Pile Thickness .134 (3.4 mm)

Average Density 7,522

Yarn Weight Tufted 28 oz./yd.2 (949 g./m.2)

Primary Backing Polypropylene

Secondary Backing Woven Polypropylene with

Post Consumer Recycled Content

Width 12 feet (3.66 m.)
Pattern Repeat Random Match

Total Recycled Content 2.50%

PERFORMANCE

Static ControlLess Than 3.5 K.V. StepFlame ResistancePasses (DOC FF-1-70)Flooring Radiant PanelClass 1 (ASTM E-648)Smoke DensityLess than 450 (ASTM E-662)Soil ResistanceCommercial Anti-SoilCRI Green Label PlusCertification # GLP7078

WARRANTIES

Wear 10 Year Limited Warranty

ADDITIONAL INFORMATION

Custom Colors

Backing Options

Coordinating Styles

Contact Sales Representative
See iLoc® backings at
www.cambridgecarpet.com

Coordinating StylesMultipleSamples800 451 1250





Specifications are based on averages from manufacturing processes and may vary within normal industry tolerances. Components may be changed without notice due to raw material shortages and/or technological advances. Such variances do not affect performance.

Carpet Design® 2003 Beaulieu Group, LLC.

BILTMOREIII

style # 6BLT



201 Princeton Boulevard P.O. Box 1110 Adairsville, GA 30103 800 451 1250

335 Roxton Street Acton Vale, Quebec Canada JOH 1A0 888 467 5075

www.cambridgecarpet.com

A Beaulieu Commercial Brand