

Japanese ceremony is a simple line between protocol and the human intellect. Western flourishes do not apply. Such it is with Ceremony. Simple metallic lines connect directly to visual beauty.

| | US UNITS | METRIC UNITS |
|---|--|--|
| Total Weight | 21.0 oz PLY 14.0 oz PSY | 651 g PLM 475 g PSM |
| Roll Width | 54 in. | 137 cm |
| Gauge | 22 Mils | 0.55 mm |
| Fabric | Osnaburg | |
| Tensile (Minimum) | 50 x 55 lb _f | 222 x 245 N |
| Tear (Minimum) | 25 x 25 | |
| Federal Spec | CCC-W-408A, Type II | |
| CFFA Spec | CFFA-W-101-D, Type II | |
| Fire Testing | NFPA 101® Life Safety Code® NFPA255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover UL Labeled and Listed | |
| Repeat | Vertical Horizontal Match Information | 33 in. 27 in. Match Vertical Lines, Reverse Hang |
| 1 When applied to GRC Board with A-848-B adhesive | | 2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive |

Available in 10 Colorways

- | | |
|-------------------------|-----------------------|
| *CM21-40 Amber | *CM21-15 Prism |
| *CM21-09 Copper Springs | *CM21-51 Royal Plum |
| *CM21-11 Desert Sun | *CM21-24 Seed Pearl |
| *CM21-74 Galaxy | *CM21-32 Stardust |
| *CM21-19 Honey Gold | *CM21-56 Tawny Copper |

* These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners (ex. Lestoil®) have the potential to damage the surface of the wallcovering along with excessive scrubbing.