



Sanitas Wallcoverings are manufactured by:
RJF International Corporation
 3875 Embassy Parkway
 Fairlawn, Ohio 44333

Sanitas Wallcoverings
FACT SHEET
Pattern Name: Pentimento©

| QUIK SPEC | U.S. UNITS | METRIC UNITS |
|---------------------------------------|--|---------------------|
| <i>Total Weight:</i> | 21 oz. PLY | 651 g. PLM |
| | 14 oz. PSY | 474 g. PSM |
| <i>Roll Width:</i> | 53/55 in. | 134/140 cm. |
| <i>Gauge (average):</i> | 0.021 in. | 0.53 mm. |
| <i>Fabric:</i> | Osnaburg | |
| <i>Tensile (minimum):</i> | 50 x 55 lb _f | 222 x 245 N |
| <i>Tear (minimum):</i> | 25 x 25 | |
| <i>Federal Spec:</i> | CCC-W-408A, Type II | |
| <i>CFFA Spec:</i> | CFFA-W-101D, Type II | |
| <i>Fire Testing:</i> | NFPA 101 [®] Life Safety Code [®] NFPA 255 (ASTM E-84 CAN S102M) Tunnel Test ¹ - Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover U.L. Listed and Labeled | |
| <i>Repeat: Horizontal</i> | N/A | |
| <i>:Vertical</i> | N/A | |
| <i>Nominal Pattern Width:</i> | 52 in. | 132 cm |
| <i>Special Instructions (if any):</i> | | |
| <i>Hanging Instructions:</i> | Random (Reverse) | |
| | 1. When tested on GRC board with A-848-B adhesive 2. When tested on 5/8" type X gypsum board with Koroseal [®] A-848-B adhesive | |

COLORLINE (PATTERN NUMBER/NAME OF COLORS)

Available in 17 colors

Pattern Description: The look and feel of layers of antiquity, reminiscent of ancient frescoed walls.

| | | |
|-------------------|------------------|--------------------|
| 4P21-21 Mattia | 4P21-96 Viviano | 4P21-88 Carovaggio |
| 4P21-41 Artemisia | 4P21-11 Luca | 4P21-13 Cappella |
| 4P21-35 Valentin | 4P21-64 Gregorio | 4P21-56 Vittoria |
| 4P21-04 Palma | 4P21-45 Carel | 4P21-38 Laurent |
| 4P21-57 Pietro | 4P21-60 Annibale | 4P21-20 Alessandro |
| 4P21-82 Gian | | 4P21-85 Marinali |

Notes:

- "Pattern Width" is the trim width on the specification and represents the width of the wallcovering that will be received by the customer.
- "Gauge" is the product thickness measured after the first pattern colorway is produced.
- "Tensile" and "Tear" results are the minimums required by CCC-W-408A federal specifications.
- "Nominal Pattern Width" is the expected width yield from one drop on the wall.