Test Number: 253110

Independent Textile Testing Service, Inc.

P.O. Box 1948 1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: ittslab@dalton.net

TEST REPORT

Customer: Masland Carpets, Inc. April 29, 2005

Subject: Specimens of the submitted sample were prepared and tested in accordance with ASTM E 648-03 and/or Federal Test Method 372. NFPA 253

FLOORING RADIANT PANEL TEST

Sample Description

Style: 7820 Ambient

GSA SIN Number: 31-301: Broadloom Carpet

Test Assembly

Mounted on 6mm FRC Board
(Using Parabond M433 Adhesive)

Test Results	Specimen No. 1	Specimen No. 2	Specimen No. 3
Critical Radiant Flux	0.71 watts/cm^2	0.71 watts/cm^2	0.71 watts/cm^2
Total Burn Length	30.0 cm	30.0 cm	30.0 cm
Flame Front Out	15.0 minutes	13.0 minutes	13.0 minutes

Average Critical Radiant Flux	**0.71**	**watts/cm^2**
Estimated Standard Deviation	**0.0**	**watts/cm^2**
	0.0%	**coefficient of variation**

L. Kent Suddeth
Executive Vice President

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of Independent Textile Testing Service, Inc., must receive our prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of the Independent Textile Testing Service, Inc., are not to be used under any circumstances in advertising to the general public.

LH2 10M (10/00)