

Additional Finishes

Bernhardt Textiles will, as an accommodation to customers and at the customer's own risk, have special finishes or backing applied to our fabrics at an additional net charge.

Fabrics will shrink when processed so yardage should be increased by 10% to insure correct and final length.

Bernhardt Textiles takes no responsibility for the work of any finisher nor any resultant shrinkage, coloration change or damage to the fabric.

Please allow two weeks for processing.

Acrylic Backing

A back coating that provides stability, eliminates fraying, and prevents adhesive bleed through.

5-54 yards	Minimum \$125.00
55 yards or more	\$2.50 per yard net

Stain Resistant Finish

A soil and stain resistant finish for upholstery and panel fabrics.

5-54 yards	Minimum \$100.00
55 yards or more	\$2.00 per yard net

Flame Retardant Treatment

Contact your Bernhardt Textiles Account Executive.

Nano-Tex®

A long-lasting spill and stain resistant finish.

Contact your Bernhardt Textiles Account Executive for a list of pre-approved patterns.

5-30 yards	Minimum \$150.00
31 yards or more	\$3.50 per yard net

Nano-Tex® with DuraBlock™

A stain resistant finish and a breathable moisture barrier. Contact your Bernhardt Textiles Account Executive for a list of pre-approved patterns.

5-25 yards	Minimum \$200.00
26 yards or more	\$9.00 per yard net

DuraBlock™

A breathable moisture barrier applied to in-stock Nano-Tex® patterns. Contact your Bernhardt Textiles Account Executive for a list of pre-approved patterns.

5-25 yards	Minimum \$200.00
26 yards or more	\$7.00 per yard net

Note: Other finishes and backings may be available in addition to those listed above.

Contact your Sales Representative for a quote or further information regarding any other additional finish. Bernhardt Textiles does not warrant additional finishes.

Custom Fabrics

Custom fabrics are sold only by the full piece and sizes vary according to the mill. The customer is responsible for purchasing all production overage. Bernhardt Textiles reserves the right to charge a strike-off fee for custom fabrics. Invoices will reflect actual yardage shipped.

Bernhardt Textiles will work with the customer to develop special colors and fiber constructions of standard fabrics. When a custom fabric is needed contact your Sales Representative for pricing and minimum yardage requirements.

Additional lead time is required for custom work and a 50% deposit must be received by Bernhardt Textiles before production of fabric will begin. **All custom fabrics are subject to a 10% upcharge.**

Limited Warranty

Bernhardt Textiles does not warrant or guarantee fabrics or leathers against fading, shrinking, stretching, seam slippage, wear abrasion, wrinkling, creasing, staining, running or discoloration from contact with any liquid or alteration in color and hand due to any finish treatment.

Bernhardt Textiles is not responsible for dye lot differences or discrepancies in widths of fabrics and does not guarantee, warrant or represent exact matches to cuttings, memos and samples. Fiber content and/or yarns may be substituted at our discretion. Fabric sources may be changed without notification.

Leather hides may contain marks, scars, scratches or wrinkles considered by the tanneries to be naturally inherent and acceptable characteristics. Bernhardt Textiles takes no responsibility for the size or location of such marks.

While Bernhardt Textiles will supply customer, upon request, with copies of results of independent testing done on its textiles, Bernhardt Textiles does not guarantee the results of such testing or that its products will meet specific industry, government or other

codes or standards. Quality and expert design are utilized in the manufacture of Bernhardt Textiles. Our products are made in accordance with the Textile Fiber Products Identification Act and meet or exceed the industry standards as defined by the Association of Contract Textiles (A.C.T.) guidelines. Under normal conditions our products perform for their intended purpose in accordance with industry standards. All warranties are void if fabric care instructions are not followed properly and we will not be liable for product abuse. The above warranty is given expressly and in lieu of any other warranties either express or implied, including any warranties of merchantability or fitness for a particular purpose and shall expire fully three (3) years from the date of purchase of the product.


Flammability Notice

Bernhardt Textiles does not warrant or assume any responsibility for flame retardant properties of fabrics or leathers, or issue any certificates regarding flammability. All Bernhardt Textiles contract fabrics meet the standards as set forth in the California Technical Bulletin #117. Some fabrics meet other flammability standards as are listed on the swatch cards and in this price list. Bernhardt Textiles is not responsible for the final product resulting from any type of special finishing or flammability treatment. If in doubt of the suitability of a particular fabric, it is the suggestion of Bernhardt Textiles to submit a fabric sample to the fire regulatory authorities with jurisdiction at the final installation site.

General Services Administration


Products not available on the Bernhardt GSA - Federal Supply Service Contract GS-28F-7040G are noted in the product description.

For information regarding GSA pricing, please visit Bernhardttextiles.com.

fire retardancy 



Flammability testing determines a fabric's resistance to burning.

Upholstery	California Technical Bulletin #117 Section E
Direct Glue Wallcoverings	ASTM E 84-07 (adhered method)
Panels and Upholstered Walls	ASTM E 84-07 (unadhered method)
Drapery	N.F.P.A. 701 Method 1

colorfastness to light 

Colorfastness to light is the degree to which fabric will retain its color when exposed to light.

Upholstery	AATCC 16 Option 1 or 3-2003 Class 4 Minimum at 40 hours
Direct Glue Wallcoverings	AATCC 16 Option 1 or 3-2003 Class 4 Minimum at 40 hours
Panels and Upholstered Walls	AATCC 16 Option 1 or 3-2003 Class 4 Minimum at 40 hours
Drapery	ASTM 16 Option 1 or 3-2003 Class 4 Minimum at 40 hours

abrasion  heavy duty  general contract

Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as a heavy duty specification.

General Contract	ASTM D4157-02 (ACT approved #10 cotton duck) 15,000 double rubs Double Rubs Wyzenbeek Method or ASTM D4966-98 (12 KPa pressure) 20,000 cycles Martindale method
Heavy Duty Upholstery	ASTM D4157-02 (ACT approved #10 cotton duck) 30,000 double rubs Double Rubs Wyzenbeek method or ASTM D4966-98 (12 KPa pressure) 40,000 cycles Martindale method

colorfastness to wet & dry crocking 

Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other materials and can occur under wet or dry conditions.

Upholstery	AATCC 8-2001 Dry Crocking, Class 4 minimum Wet Crocking, Class 3 minimum
Direct Glue Wallcoverings	AATCC 8-201 Dry Crocking, Class 3 minimum Wet Crocking, Class 3 minimum
Panels and Upholstered Walls	AATCC 8-2001 Dry Crocking, Class 3 minimum Wet Crocking, Class 3 minimum
Drapery	AATCC 8-2001 (solids) Dry Crocking, Class 3 minimum Wet Crocking, Class 3 minimum AATCC 116-2001(prints) Dry Crocking, Class 3 minimum Wet Crocking, Class 3 minimum Class 3 minimum

physical properties 

Piling is the formation of fuzzy balls of fiber on the surface of a fabric that remain attached to the fabric. Breaking strength is the measurement of stress exerted to pull a fabric apart under tension. Seam slippage is the movement of yarns in a fabric that occurs when it is pulled apart at a seam.

Upholstery	Brush pill ASTM D3511-02, Class 3 minimum Breaking strength ASTM D5034-95(2001) (Grab Test) 50 lbs. minimum in warp & weft Seam slippage ASTM D4034 25 lbs. minimum in warp & weft
Panels and Upholstered Walls	Breaking strength ASTM D5034-95(2001) (Grab Test) 35 lbs. minimum in warp & weft
Drapery	Seam slippage ASTM D3597-434-75 for fabrics over 6oz./sq. yard, 25 lbs. min. in warp & weft Seam slippage ASTM D3597-02-D434-95 for fabrics under 6oz./sq. yard, 25 lbs. min. in warp & weft

cleaning codes

Code S

Recommended Cleaning Instructions

To prevent overall soil, frequent vacuuming or light brushing to remove dust and grime is recommended. Spot clean, using a mild water-free solvent or dry cleaning product. Clean only in a well ventilated room and avoid any product containing Carbon Tetrachloride or other toxic materials. Pretest small area before proceeding. Cleaning by a professional furniture cleaning service only is recommended.

Caution: Never remove cushion covers for separate dry cleaning or washing, even though they do have zippers. Do not use bleach at any time. The use of steam or water-based cleaners may cause excessive shrinking or staining of this particular fabric. Do not use any tumble method of cleaning service as this may destroy the backing of the fabric or shrink or otherwise damage the upholstery fabric.

Code W

Recommended Cleaning Instructions

To prevent overall soil, frequent vacuuming or light brushing to remove dust and grime is recommended. Spot clean, using the foam only from a water-based cleaning agent such as a mild detergent or non-solvent upholstery shampoo product. Apply foam with a soft brush in a circular motion. Vacuum when dry. Pretest small area before proceeding. Use a professional furniture cleaning service when an overall soiled condition has been reached.

Caution: Never remove cushion covers for separate dry cleaning or washing, even though they do have zippers. Do not use bleach or any tumble method cleaning as this may destroy the backing of the fabric or shrink or otherwise damage the upholstery fabric.

Code WS

***Recommended Cleaning Instructions**

To prevent overall soil, frequent vacuuming or light brushing to remove dust and grime is recommended. Spot clean, with a mild solvent, an upholstery shampoo, or the foam from a mild detergent. When using a solvent or dry cleaning product, follow instructions carefully and clean only in a well ventilated room. Avoid any product which contains Carbon Tetrachloride or other toxic materials. With either method, pretest a small area before proceeding. Use a professional furniture cleaning service when an overall soiled condition has been reached.

Caution: Never remove cushion covers for dry cleaning or washing, even though they do have zippers. Do not use bleach or tumble method cleaning service as this may destroy the backing of the fabric or shrink or otherwise damage the upholstery fabric.

***Bleach Cleanable Fabrics:** Specific instructions are provided in the price list for bleach cleanable patterns. Reference the individual pattern for water/bleach ratio and extraction information.

Code X

Recommended Cleaning Instructions

Clean this fabric only by vacuuming or light brushing to prevent accumulation of dust or grime. Water-based foam cleaners or solvent-based cleaning agents of any kind may cause excessive shrinking, staining or distortion of the surface pile and, therefore, should not be used.

Caution: Never remove cushion covers for separate dry cleaning or washing, even though they do have zippers. Do not use any tumble method or cleaning service as this may destroy the backing of the fabric or shrink or otherwise damage the upholstery fabric.