TECHNICAL CHARACTERISTICS WALLPAPER

CARACTERÍSTICAS TÉCNICAS

WEIGHT AND DIMENSIONS *TABLA DE MEDIDAS Y PESO*

SIZE *TAMAÑO*	VITREO · BRILLANTE SHINING · AUREO 3/4″ x 3/4″ · *2 x 2 cm* LUX · SUNSHINE · AUREO 5/8″ x 5/8″ · *1.5 x 1.5 cm*
THICKNESS *ESPESOR*	5/32″ · *~ 4 mm*
SHEET SIZE *MEDIDAS HOJAS*	12 7/16″ x 12 7/16″ *31.6 x 31.6 cm*
JOINT *JUNTA*	2/48″ · *~ 1 mm*
WEIGHT *PESO*	~ 1.6 lb/ SQF · *~ 7 kg/ m²*
SHEETS PER BOX *HOJAS POR CAJA*	20
WEIGHT PER BOX *PESO POR CAJA*	~ 34.45 lbs· *~ 15.66 kg*
QUANTITY PER BOX *CANTIDAD POR CAJA*	21.528 SQF · *2 m²*
SIZE OF THE BOX *TAMAÑO DE CAJA*	13″ x 13″ x 4″ · 33 x 33 x 10.16 cm

· Colors may vary somewhat by production lot.
· *Los colores pueden presentar variaciones según el lote.*

ASTM TESTS

TEST PERFORMED AND REQUIREMENTS	RESULTS
Range of thickness (ASTM C499)	3.91 mm
Facial dimensions (ASTM C499)	19.98 mm
Wedging (ASTM C502)	0.0%
Thermal shock (ASTM C484)	Resistant
Bond strength (ASTM C482)	passes
Crazing (ASTM C424)	passes
Friction coefficient (ASTM C1028-96)	Dry condition 0.76 Wet condition 0.61
Water absorption (ASTM C373)	0.08%
Apparent porosity (ASTM C373)	0.20%
Apparent specific gravity (ASTM C373)	g/cm 3:2.37
Bulk density (ASTM C373)	g/cm 3:2.36
Frost resistance (ASTM 1026)	Resistant
Chemical resistance (ASTM 543)	Resistant
Color resistance to fading (DIN 51094)	Resistant
Coefficient of linear thermal expansion (ASTM D696)	Negligible (dilation is absorbed by grout)
Resistance to fire	Non-combustible - Class O (emits no toxic gas at melting)
Wedging of flat, rectangular, ceramic wall and floor tile (ASTM C502-93A)	0.0%

up to
55%
Recycled Glass