TABLE I - DESCRIPITON OF MATERIAL TESTED

Identification
Type Material
Total Weight

Mohair Velvet

Fabric

- 18.6 ounces per square yard

TABLE II - TEST RESULTS

Test Specimen	Flame Spread Index	Smoke Density Developed
GRC board	0	0
red oak flooring	100	100
Mohair Velvet	20	5

Although deleted from the Standard in 1977, some agencies may require Fuel Contribution for approval of a material. While ASTM E 84-86 makes no provision for measuring Fuel Contribution, it may be calculated in accordance with E 84-75. For the material tested, Fuel Contribution is 0 when calculated in this manner.

TABLE III - OBSERVATIONS DURING TESTING

Ignition over the burners was noted at 0.20 minutes. The flame front advanced to a maximum of 4.5 feet at 0.36 minutes with a maximum temperature recorded during the test of $576^{\circ}F$.