





MARAZZI  **USA**

the fine art of porcelain stoneware


(jade)

glazed porcelain stoneware


Made In The USA




Chestnut




Ochre



Sage



Taupe



Chestnut Mosaic - Square 1"x1"



Ochre Mosaic - Square 1"x1"




Sage Mosaic - Square 1"x1"




Taupe Mosaic - Square 1"x1"



Chestnut Mosaic - Square 2"x2"



Ochre Mosaic - Square 2"x2"



Sage Mosaic - Square 2"x2"



Taupe Mosaic - Square 2"x2"




Chestnut Mosaic - Brick 1"x2"



Ochre Mosaic - Brick 1"x2"



Sage Mosaic - Brick 1"x2"



Taupe Mosaic - Brick 1"x2"



ASTM Test Results

Technical Characteristics	ANSI Standards	ASTM Test Results	ASTM Test Methods
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7	MOHS Scale
Breaking Strength	≥ 250 lbf.	≥ 420 lbf.	C648
Facial Dimension	-3.0% < Nominal ≤ 3.0%	Within Standard	C499
Nominal Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (squareness)	+/- 0.50% or +/- 2.0 mm**	Within Standard	C502
Warpage (flatness)	+/- 0.75% or +/- 2.3 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF-Dynamic Coefficient of Friction (Wet Areas Only) [†]	As Reported	Minimum 0.42	DCOF AcuTest SM *
SCOF-Static Coefficient of Friction (Dry)	As Reported	0.70 ≤ S.C.O.F. < 0.80	C1028
SCOF-Static Coefficient of Friction (Wet)	As Reported	0.60 ≤ S.C.O.F. < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

[†] Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatile.com for complete information regarding the DCOF AcuTest test method and values.

* DCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.

** Whichever is less

	MODULAR TILE	FLOOR TILE	DECOS	TRIMS*
Thickness	6 1/2"x6 1/2" (16.5x16.5 cm) 5/16" (8.5mm)	13"x13" (33.3x33.3 cm) 5/16" (8.5mm)	20"x20" (50x50 cm) 7/16" (11mm)	13"x13" (33.3x33.3 cm) Mosaic - Square 1"x1"
Names (colors)	UE4R	UE3A	UE3E	UE4V
Chestnut	UE4S	UE3B	UE3F	UE4W
Ochre	UE4T	UE3C	UE3G	UE4X
Sage	UE4U	UE3D	UE3H	UE4Y
Taupe	UE4V	UE3E	UE3I	UE4Z
				UE45
				UE46
				UE47
				UE48
				UE3J
				UE3K
				UE3M
				UE3N

Notes: * Trim is available in all colors and made to complement Modular and Floor Tile.