

LOBA®



WS 2K Supra



Description:

LOBA® WS 2K Supra is a high quality two-component waterborne polyurethane finish for use on high traffic residential, commercial and institutional wood floors. LOBA® WS 2K Supra is our most durable wood floor finish.

LOBA® WS 2K Supra is an international favorite since being introduced in 1994. LOBA® WS 2K Supra levels beautifully and has proven durability in luxury homes, museums, restaurants, offices and hotels in over 50 countries

Features:

- Waterborne Polyurethane formula with excellent wear resistance
- Easy to mix, no tools needed
- Excellent build through high solid content
- No bubbling, beautiful leveling and flow
- Easy to use, can be applied by T-Bar applicator, brush, lambswool or roller
- Non yellowing
- Available in extra matte, semi-gloss, satin
- VOC compliant
- Fast Drying
- No lap marks and streaks
- Perfect for cork floors because of high elasticity
- Water clean-up
- Non-yellowing

Recommended Use:

High Traffic Residential:

Active homes with pets and children which are exposed to heavy wear

Commercial:

Offices, restaurants, schools, retail stores and public areas

LOBA® WS 2K Supra Technical Data



Gloss Level:	Extra matte (10°), Satin (20°), semi-gloss (40°)
Package Size:	1 US gallon
VOC Content	Satin and semi-gloss: < 200 grams per liter Extra matte: < 100 grams per liter LOBA® WS 2K Supra qualifies for LEED credit
Range of Use:	Wood and cork floors exposed to heavy wear
Before Use:	Read all instructions and MSDS. Do not thin the product. Keep from freezing. Floor must to be free from wax, oil, dust or dirt. Shake well before use! Add hardener ratio 10 : 1, and mix it by shaking
Finishing process:	Prepare surface according to NOFMA-accepted method Apply LOBA® WS EasyPrime and allow to dry thoroughly. Apply LOBA® WS 2K Supra and allow to dry thoroughly. Screen with 150 grit screen or maroon pad Apply LOBA® WS 2K Supra
Application Tools:	T-Bar Applicator, Lambswool, Brush or Roller
Coverage:	350 - 400 square feet per gallon
Dry time:	2 – 3 hours, light wear after 24 hours, reaches final hardness after approx. 5 days
Intercoat Abrasion:	Can be recoated without intercoat abrasion within 24 hours.
Thinner:	The finish is ready-to-use. Do not thin. If necessary the drying can be delayed by adding a maximum of 5% LOBA® WS Argo . Add LOBA® WS Argo only after adding hardener to the varnish.
Storage and Transportation	Store and transport between 41°F to 77°F. Shelf life 12 months in unopened container.
Drytime Retarder	LOBA® WS Argo can be added to all LOBA water based finished to prevent lap marks When applied under unfavorable conditions such as low air humidity or high temperatures.
Recoating of Prefinished Wood Floors	Prefinished wood floors can be recoated without sanding if LOBA® WS 2K Contact primer is used as adhesion promoter before coating. We recommend to topcoat LOBA® WS 2K Contact with LOBA® WS 2K Supra to achieve a comparable durability to modern UV-curing finishes.
General Information	The general Information on the use of LOBA products is part of this information and should be read before applying Loba products. When this product is used in combination with other LOBA products also the technical information of these products has to be followed. While Information and data contained herein is presented in good faith and is believed to be reliable, they do not constitute any part of our terms and conditions of sale. Applicator or end user is required to read and understand all information contained on package labels. Additional technical information is also available by visiting our website. If any results achieved during application are less than satisfactory, stop application and contact our technical department.

Loba-Wakol, LLC
1604 N. Main St.
Kannapolis, NC 28081
Phone (800) 230-6456
Fax (704) 932-3041
www.loba-wakol.com

revised: June 2009

