

OXYGEN

Float

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

36" X 36" (91.4 x 91.4 cm)

Yarn TypeMilliken-Certified WearOn® Nylon
Type 6,6**Stain Repel / Stain Resist / Soil Release**

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Millitron®

Tufted Face Weight20 oz/yd² (678 g/m²)**Gauge**

1/10

Stitches Per Inch

10.3

Tufts103/in² (1,595/100 cm²)**Finished Pile Height**

0.14" (3.56 mm)

Finished Pile Thickness

0.11" (2.79 mm)

Average Density (Finished)

7,793

Standard BackingPVC-Free Comfort Plus® ES Cushion
Available with TractionBack®**Recycled Content by Total Weight**ES Backing: 35.9% Pre-Consumer,
0.0% Post-Consumer
ESP Backing: 27.3% Pre-Consumer,
10.0% Post-Consumer**Nominal Total Thickness**

0.35" (8.9 mm)

Nominal Total Weight104 oz/yd² (3,526 g/m²)**Flammability (Radiant Panel****ASTM-E-648)**

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or**ASTM-E-662)**

≤ 450

**Methenamine Pill Test (CPSC FF-1-70
or ASTM D 2859**

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

**Static Electricity (AATCC-134) 20%
R.H., 70° F.**

≤ 3.5 KV, Permanent Conductive Fiber

**Texture Appearance Retention Rating
(TARR)**

Severe Traffic End-Use Applications

Recommended MaintenanceMilliCare® Textile and Carpet Care
Service Network**Indoor Air Quality—CRI Green Label
Plus™**

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic, Ashlar, Quarter-Turn

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.