



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 31328

Date: 10-28-2008

For the Account Of: Carnegie
110 North Centre Avenue
Rockville Center, NY 11570
Contact: Charles Griffin

Client's Identification: 4350

Test Performed NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2004 – Test #1

TEST DATA

Specimen #	Initial Mass(g)	Final Mass(g)	% Weight Loss	Flaming Drip Seconds	Afterflame Seconds
1	13.5	8.9	34%	1	0
2	13.4	8.9	34%	0	0
3	13.2	9.0	32%	0	0
4	13.2	8.9	33%	1	0
5	13.3	9.0	32%	0	0
6	13.3	9.0	33%	0	0
7	13.4	9.0	33%	1	0
8	13.3	8.9	33%	0	0
9	13.3	10.4	22%	0	0
10	13.4	9.6	28%	1	0
Average	13.3	9.2	31%	0.4	0.0

Approximate weight (oz./sq. yd): 6.496

Product Configuration: ☒ Single Layer ☐ Multi Layer

SD = Standard Deviation 3 SD = Mean + 3 SD g/m /(divided) x .835 = oz/yd

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

- Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing. (Flaming Drip)
- Where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing.
- Individual specimens will be listed as a failure if it exceeds mean + 3 SD
- Where the specimens do not demonstrate performance in accordance with either of the conditions indicated above, the material shall be recorded as passing this test and shall be designated as flame resistant.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Complies
☐ Does Not Comply
☐ Testing of 10 additional specimens is required

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature