

COMMERCIAL TESTING COMPANY

Post Office Box 985 • 1215 South Hamilton Street • Dalton, Georgia 30722 Telephone (706) 278-3935 • Facsimile (706) 278-3936

Report Number 02-03314.2

Masland Carpets, Inc. Saraland, Alabama Test Number 3318–9632–B March 20, 2002

Smoke Density Test

Test Method: The test was conducted in accordance with the ASTM fire test response standard E 662–01, Specific Optical Density of Smoke Generated by Solid Materials. It provides a means of determining specific optical density of smoke generated by materials mounted in a vertical position. Results are expressed in terms of specific optical density. The method employs an electrically heated radiant–energy source positioned so as to produce an irradiance level of 2.5 W/cm² over the center of a vertically mounted 76.2 mm square specimen. This exposure provides the nonflaming condition of the test. For the flaming condition, a six–tube burner is used to apply a row of equidistant flamelets across the lower edge of the specimen in addition to the specified irradiance level from the heating element. Specimens are exposed to the flaming and nonflaming conditions within a closed chamber while varying light transmission is measured using a photometric system with a vertical light path. These measurements are used to calculate specific optical density of the smoke generated during the time period to reach the maximum value.

Material Tested:

Identification: 7811 Verve

Construction: Cut/Uncut Pile

Secondary Backing: Woven Synthetic

Color: 18100 Hall of Frame

Total Weight: 64.5 oz/yd²

Test Result:

| | Flaming Exposure | | | Non-Flaming Exposure | | |
|-----------------------------|------------------|---------|-----|----------------------|------|------|
| Specimen | #1 | #2 | #3 | #1 | #2 | #3 |
| Ds @ 1.5 minutes | 18 | 14 | 15 | 1 | 1 | 1 |
| Ds @ 4.0 minutes | 143 | 127 | 117 | 77 | 71 | 50 |
| Dm | 143 | 127 | 117 | 461 | 386 | 216 |
| Time to Dm | 3.6 | 3.4 | 2.8 | 16.9 | 13.9 | 16.8 |
| Dc | 14 | 11 | 11 | 4 | 1 | 2 |
| Dm (corrected) | 129 | 115 | 106 | 457 | 385 | 215 |
| Average Ds @ 1.5 minutes 16 | | | | 1 | | |
| Average Ds @ 4.0 minutes | | 129 | | 66 | | |
| Average Dm | | 129 354 | | | | |
| Average Dm (corrected) | | 117 | | | 352 | |

Commercial Testing Company

(Authorized Signature)

The ASTM E 662 test procedure of Commercial Testing Company is recognized by the United States Department of Commerce, National Institute of Standards and Technology (NIST), through the National Voluntary Laboratory Accreditation Program (NVLAP) for compliance with Title 15 of the Code of Federal Regulations, Part 285. These criteria encompass the requirements of ISO/IEC Guide 25 and the relevant requirements of ISO 9002 (ANSI/ASQC Q92–1987). This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.