



**Professional
Testing
Laboratory
Inc.**

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	1 of 2

CLIENT	CORPORATE/DIV. OF SHAW
---------------	------------------------

TEST METHOD CONDUCTED	AATCC Test Method 134-1996 Electrostatic Propensity of Carpets
------------------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

TEST RESULTS

MAXIMUM VOLTAGE	NEG 1.3 KV
------------------------	------------

GENERAL PRINCIPLE

This method is designed to assess the static propensity of flooring material by controlled laboratory simulation of conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

A flooring material preconditioned to equilibrium at controlled atmospheric conditions is walked on by a test subject in a specified manner with specified shoe soles. The static charges which build up on the tester are monitored continuously by a recorder.

A neolite shoe sole has been chosen as the primary reference material because its static performance is much like that of many common leathers. It is a commonly used shoe sole material and can be easily cleaned, while its chemical and physical properties are quite uniform.

A chrome tanned leather shoe sole has been chosen for a secondary reference material because it is representative of a certain class of leathers whose performance differs significantly from that of neolite soles on certain carpet fiber. Statistically, chrome tanned leather comprises a very small percentage of the shoe sole market, but must be considered in critical applications.

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





**Professional
Testing
Laboratory
Inc.**

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	1 of 2

CLIENT	CORPORATE/DIV. OF SHAW
--------	------------------------

TEST METHOD CONDUCTED	ASTM E662-01 Specific Optical Density of Smoke Generated by Solid Materials, also referenced as NFPA 258
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	-----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	-----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

TEST RESULTS

FLAMING	324
---------	-----

GENERAL PRINCIPLE

This procedure is designed to measure the specific optical density of smoke generated by the test specimen within a closed chamber. Each specimen is exposed to an electrically heated radiant-energy source positioned to provide a constant irradiance level of 2.5 watts/square cm on the specimen surface. Measurements are recorded through a photometric system employing a vertical beam of light and a photo detector positioned to detect the attenuation of light transmittance caused by smoke accumulation within the chamber. The light transmittance measurements are used to calculate specific optical density, a quantitative value which can be factored to estimate the smoke potential of materials. Two burning conditions can be simulated by the test apparatus. The radiant heating in the absence of ignition is referred to as the Non-Flaming Mode. A flaming combustion in the presence of supporting radiation constitutes the Flaming Mode.

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





Professional
Testing
Laboratory
Inc.

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	2 of 2

CLIENT	CORPORATE/DIV. OF SHAW
--------	------------------------

TEST METHOD CONDUCTED	ASTM E662-01 Specific Optical Density of Smoke Generated by Solid Materials, also referenced as NFPA 258
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	-----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	-----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

CONDITIONS	
PREDRYING OF TEST SAMPLE CONDITIONING OF TEST SAMPLE	24 Hours at 140 degrees F 24 Hours at 70 degrees F and 50% relative humidity

FURNACE VOLTAGE CHAMBER TEMPERATURE TEST MODE	115 V 95 degrees F Flaming	IRRADIANCE CHAMBER PRESSURE	2.5 watts/sq cm 3" H2O
---	----------------------------------	--------------------------------	---------------------------


AVERAGE MAXIMUM DENSITY CORRECTED (Dmc)	324
---	-----

	1	2	3
Maximum Density (Dm)	381	328	386
Time to Dm (minutes)	3.5	3.0	3.5
Clear Beam (Dc)	43	39	42
Corr. Max Density (Dmc)	338	289	344
Density at 1.5 minutes	37	109	79
Density at 4.0 minutes	373	312	381
Time to 90% Dm (minutes)	2.5	2.5	3.0
Specimen Weight (grams)	14.5	13.9	14.1

AVERAGE SPECIFIC OPTICAL DENSITY AT 4.0 MINUTES: 355
--

APPROVED BY: 

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





**Professional
Testing
Laboratory
Inc.**

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	1 of 2

CLIENT	CORPORATE/DIV. OF SHAW
TEST METHOD CONDUCTED	ASTM E648-00 Critical Radiant Flux of Floor Covering Systems Using A Radiant Heat Energy Source, also referenced as NFPA 253 and FTM Standard 372

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	-----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	-----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

This test report relates to the installation in accordance with the criteria set forth in the report. Any variation in the criteria may produce different results.

TEST RESULTS

AVERAGE CRITICAL RADIANT FLUX	.48 Watts/Square Cm*
-------------------------------	----------------------

GENERAL PRINCIPLE

This procedure is designed to measure the critical radiant flux at flame out, of horizontally mounted floor covering systems exposed to a flaming ignition in a test chamber which provides a graded radiant heat energy environment. The imposed radiant flux simulates the thermal radiation levels likely to impinge on the floors of a building whose upper surfaces are heated by flames of compartment. The test result is an average critical radiant flux (watts/square cm) which indicates the level of radiant heat energy required to sustain flame propagation in the flooring system. Theoretically, if a room fire does not impose a radiant flux that exceeds this critical level on a corridor floor covering system, flame spread will not occur.

The NFPA Life Safety Code 101 specifies as Class 1 Critical Radiant Flux of .45 watts/sq cm or higher and Class 2 Critical Radiant Flux as .22 - .44 watts/sq cm.

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





Professional
Testing
Laboratory
Inc.

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	2 of 2

CLIENT	CORPORATE/DIV. OF SHAW
--------	------------------------

TEST METHOD CONDUCTED	ASTM E648-00 Critical Radiant Flux of Floor Covering Systems Using A Radiant Heat Energy Source, also referenced as NFPA 253 and FTM Standard 372
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	-----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	-----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

This test report relates to the installation in accordance with the criteria set forth in the report. Any variation in the criteria may produce different results.

FLOORING SYSTEM ASSEMBLY	
SUBSTRATE UNDERLAYMENT ADHESIVE	Mineral-Fiber/Cement Board Direct Glue Down Subset 1000
CONDITIONING	Each test sample was conditioned a minimum of 96 hours at 70 ± 5° F and 50 ± 5% relative humidity.

TEST RESULTS

TEST DATA	DISTANCE BURNED	TIME TO FLAME OUT	CRITICAL RADIANT FLUX
SPECIMEN 1	37 cm	28 minutes	.53 watts/sq cm
SPECIMEN 2	42 cm	30 minutes	.44 watts/sq cm
SPECIMEN 3	40 cm	42 minutes	.48 watts/sq cm

AVERAGE CRITICAL RADIANT FLUX	.48 watts/square cm*
STANDARD DEVIATION	.05 watts/square cm
COEFFICIENT OF VARIATION	9%

*NOTE: Meets or exceeds Class 1 rating as specified in NFPA Life Safety Code 101

APPROVED BY: 

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





Professional
Testing
Laboratory
Inc.

TEST REPORT

TEST NUMBER	0082959
DATE	03/11/04
PAGE	2 of 2

CLIENT	CORPORATE/DIV. OF SHAW
--------	------------------------

TEST METHOD CONDUCTED	AATCC Test Method 134-1996 Electrostatic Propensity of Carpets
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	5A017 Shimmer UPAT
COLOR	-----
ROLL	E560241
CONSTRUCTION	Multi-Level Loop Pile
FIBER	-----
BACKING	UltraLoc Pattern
REFERENCE	TEST NO: 030204-9

TEST CONDITIONS	The sample is conditioned to equilibrium and tested at $70 \pm 2^{\circ}\text{F}$ and $20 \pm 2\%$ relative humidity.
SAMPLE PREPARATION	Tested As Received
SUBSTRATE	40 Ounce Rubberized Jute/Hair Pad

TEST RESULTS

	MAXIMUM VOLTAGE		
	DAY 1	DAY 2	AVERAGE
TEST I: Step Test/Neolite Sole	-0.6 KV	-0.8 KV	-0.7 KV
TEST II: Scuff Test/Neolite Sole	-1.2 KV	-1.3 KV	-1.3 KV
TEST III: Step Test/Leather Sole	+0.4 KV	+0.5 KV	+0.5 KV
TEST IV: Scuff Test/Leather Sole	+1.0 KV	+1.1 KV	+1.1 KV
MAXIMUM AVERAGE VOLTAGE	NEG 1.3 KV		

"The results of this test relate to the sample of flooring material tested. It's static performance may be altered in service as a result of wear, soiling, cleaning, temperature, relative humidity, etc..."

APPROVED BY: Gay Henry

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of appearance, quality or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.

