

SOUTHERN ANALOG

Panoramic

Modular Tile

Construction

Tufted, Textured Loop

Tile Sizes

50 cm x 50 cm (19.7" x 19.7")

50 cm x 1 m (19.7" x 39.4")

25 cm x 1 m (9.85" x 39.4")

Yarn Type

ECONYL® Solution-Dyed Nylon Type 6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight

15 oz/yd² (509 g/m²)

Gauge

1/12

Stitches Per Inch

10.4

Tufts

124/in² (1,920/100 cm²)

Finished Pile Height

0.13" (3.30 mm)

Finished Pile Thickness

0.072" (1.83 mm)

Average Density (Finished)

8,100

Standard Backing

PVC-Free Underscore® ES Cushion

Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 47.6% Pre-Consumer,

8.0% Post-Consumer

ESP Backing: 36.6% Pre-Consumer,

19.0% Post-Consumer

Nominal Total Thickness

0.42" (10.7 mm)

Nominal Total Weight

92 oz/yd² (3,123 g/m²)

Flammability (Radiant Panel)

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859)

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Ashlar (preferred), Monolithic, Quarter-Turn

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.