illiken,

MIDNIGHT SPARKLE

Shetland

Construction

Tufted, Textured Loop

Tile Size

36" X 36" (91.4 x 91.4 cm)

Yarn Type

Milliken-Certified WearOn® Nylon Type 6,6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Millitron®

Tufted Face Weight

 $24 \text{ oz/yd}^2 (814 \text{ g/m}^2)$

Gauge

1/8

Stitches Per Inch

8.8

Tufts

70.4/in² (1,090/100 cm²)

Finished Pile Height

0.11" (2.79 mm)

Average Density (Finished)

7,855

Standard Backing

PVC-Free Comfort Plus® ES Cushion

Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 47.3% Pre-Consumer, 0.0% Post-Consumer ESP Backing: 36.0% Pre-Consumer,

11.3% Post-Consumer

Nominal Total Thickness

0.35" (8.9 mm)

Nominal Total Weight

 $112 \text{ oz/yd}^2 (3,798 \text{ g/m}^2)$

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

< 450

Methenamine Pill Test (CPSC FF-1-70

or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

> 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%

R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label

Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®) Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency

Lifetime Floor Release Lifetime Cushion Resiliency Lifetime Moisture Resistance Lifetime Delamination of Backing Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability Lifetime Tuft Bind Lifetime Edge Ravel Flammability









This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.