

Independent Textile Testing Service, Inc.

P.O. Box 1948

1503 Murray Ave.

Dalton, Georgia 30722-1948 • Phone 706-278-3013 • Fax 706-272-7057 • E-mail: info@ittslab.com

TEST REPORT

Customer: Masland Carpets, Inc.

February 26, 2008

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Style: 7834 Sideline
Color: 38405 Dijon
Roll #: R71968840

GSA SIN Number: 31-301: Broadloom Carpet

Test Method Conducted
AATCC 134-1996
Electrostatic Propensity of Carpets

Purpose and Scope

This test method is designed to assess the static generating propensity of carpets developed when a person walks across them by controlled laboratory simulation of conditions which may be met in practice, and more particularly, with respect to those conditions which are known from experience to be strongly contributory to excessive accumulation of static charges.

Test Conditions:

Chamber Temperature: 70° F.
Chamber Relative Humidity: 20%


Test Results:	Sole	Underlay	Maximum Voltage 1 (kV)	Maximum Voltage 2 (kV)	Averages (kV)
Test I Step Test	Neolite	Plate	Neg. 1.9	Neg. 2.1	Neg. 2.0
Test II Scuff Test	Neolite	Plate	Neg. 1.0	Neg. 1.0	Neg. 1.0
Test III Step Test	Leather	Plate	Neg. 0.7	--	--
Test IV Scuff Test	Leather	Plate	Neg. 1.2	--	--

Soles: Note: AATCC 171 conducted on specimen prior to static testing as per GSA requirements.

- a) Neolite XS 664
- b) Suede Leather

Underlayment:

- a) Plate: Earth grounded metal plate
- b) H/J: Standard 40 oz./yd² rubberized Hair/Jute cushion



L. Kent Suddeth
Executive Vice President

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of Independent Textile Testing Service, Inc., must receive our prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of the Independent Textile Testing Service, Inc., are not to be used under any circumstances in advertising to the general public.