

### **COMPOSITION®**

Composition® is an acoustic wall covering available in a range of colors. Typically applied in vertical drops like wallpaper, Composition creates a surface that is pin and velcro receptive. Composition is a durable and flexible polyester wall covering that replaces the need to paint, and is easily maintained to look amazing for a long time.

Beyond all that, it creates incredible learning environments by reducing and managing the reverberation in the room, resulting in a much more peaceful space for students to learn. But it isn't just students that benefit, Composition is great for any working space.

And because not all spaces are the same we've given you creative freedom. We can cut Composition to any shape, creating something as unique as each one of us.

### **COMPOSITION®**

#### **APPLICATIONS**

- Decorative and functional acoustic wallcovering for education, retail and commercial interiors
- Minimise noise in interior environments
- Hook-and-loop surface for education and commercial sectors
- Protective layer for palsterboard
- Alternative finishing to paint


#### **SPECIFICATION**


(Wall) treatment shall be Autex Composition® from non-woven needle-punched polyester containing not less than 60% recycled material as manufactured by Autex www.autexindustries.com

Roll 0.4" - 0.5" (nom.) depth, color (\_), sound absorption: Class D, NRC 0.40, Fire rating: ASTM E-84 Class A, FS:5 - SD:25, ISO 9705: Classification: Group 1-S, AS ISO 9705 - 2003: Classification: Group 1, EN13501-1:2007+A1:2009: Classification: B - s1, d0

Install as per Autex recommendations.

If Composition is to be specified for use other than as a wallcovering, please seek guidance from your Autex Account Manager.





#### **ABSORPTION COEFFICIENT ACCORDING TO ISO 354**




Table presents the practical sound absorption coefficients as according to ISO 11654. Graph presents third octave sound absorption coefficients (According to ISO 354 Measurement of sound absorption in a reverberation room.) The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centerd on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz. and rounded to the nearest 0.05.

Frequency (Hz)	University of Auckland Test Report Number	125	250	500	1000	2000	4000	NRC	
Composition® 0.4" - 0.5"	T0814-2b	0.05	0.10	0.25	0.55	0.80	0.95	0.40	

#### **PRODUCT SPECIFICATIONS**

Product Name Composition®

Composition 100% Polyester Fiber (PET)

Roll Dimensions 48'' × 36'Tolerance (+0.2'') (+0.4'')

Thickness 0.4" - 0.5" Weight 5.51 oz/ft2

#### **INSTALLATION**

Install as per Autex recommendations. Install instructions are included in each pack or available on the website. If Composition is to be specified for use other than as a wallcovering, please seek guidance from your Autex account manager.

#### **ACOUSTIC PERFORMANCE**

Composition is specifically designed to reduce and control reverberated noise (echo) in building interiors

#### LIGHT REFLECTANCE VALUES BY COLOR

_			
Civic		57	
Citrus		49	
Myst		42	
Sanz		36	
Wasabi		33	
Lime		29	
Azure		24	
Silver		23	
Jade		22	
Porcelain		22	
Fawn		20	
Clay		20	
Granny Smith		20	
Stonewash		19	
Simba		18	
Brilliant Orange		15	
Spearmint		13	
Calypso		13	
Electric Blue		12	
Koala		12	

LRVs were measured in accordance with BS 8493:2008+A1:2010

Avocado	11
Blush	10
Sage	9
Emerald	8
Sapphire	8
Atlantis	8
Blazing Red	8
Raspberry	8
Vintage	6
Chilli Red	5
Cinder	5
Bark	5
Octane	5
Phantom	4
Theatre	3
Stately	3
Charcoal	3
Lightsout	3
Ink	3
Noir	1

#### **FIRE RATINGS**

Composition® has been evaluated using the following test methods:

ISO 9705: 1993 Classification: Group 1-S

Smoke Production Rate: <5.0m2/s
As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1 (SMOGRARC): <100m2/s2

Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015, as required by

BCA Specification C1.10-4

FI 4894 dated 6th June, 2012 and FAR 4055-2 dated 8th

October, 2013

EN13501-1:2007

B-s1, d0

Report 189053 dated 7th December, 2009

ASTM E84 - 14

Class A, FS:5 - SD:25

Report RJ3297-9R1 dated 17th March, 2015

#### **VOC EMISSIONS**

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered as a low VOC product.

VOC concentration: 0.009 mg/m3 (7 days)

#### WATER VAPOR SORPTION

ASTM C1104 / C1104M-13a

Test conditions: 49°C, 95%RH

Water vapor absorbed and adsorped after 4 days: 0.4% by weight

, , ,

#### **IMPACT RESISTANCE**

ISO 7892:1988

#### Hard Body Impact

There is no surface damage or penetration to Composition when subjected to hard body impacts. When adhered to 10mm plasterboard, the system can resist a 9-joule impact. This is equivalent to the impact of a 0.5kg object dropped from a 2m height. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5kg object dropped from a 0.5-m height.

#### Soft Body Impact

There is no surface damage or penetration to Composition when subjected to soft body impacts. When adhered to 10mm plasterboard, the system can resist a 70-joule impact. This is equivalent to the impact of a 50-kg object dropped from a 150mm height.

#### **MICROBIAL RESISTANCE**

ASTM G21-15

Growth Rating: 0 (No growth)

Composition does not promote the growth of moulds and mildew.

#### **COLOR FASTNESS TO LIGHT**

Composition is suitable for indoor use only. Light fastness is dependent on use and exposure. Composition has been evaluated to the following standard: ISO 105-B02:2014

Rating: 6 (Highest = 7)

#### **COLOR FASTNESS TO RUBBING**

ISO 105-X12:2016

Dry Rating: 4-5 (Highest = 5) Wet Rating: 4-5 (Highest = 5)

#### THERMAL PERFORMANCE

0.4" - 0.5" R.O 22 (@59°F)

#### **MOISTURE ABSORPTION**

Polyester fiber when exposed to an atmosphere of 50°C at 90% relative humidity for four days showed moisture absorption of less than 0.03% by weight. Polyester is not affected by moisture and will not rot or deteriorate in intended use situations.

#### **FABRIC CARE**

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution.

Custom printed Composition requires the services of a specialist cleaning company. Refer to the Composition Cleaning and Maintenance Guide for more information.

#### **PATTERN REPEAT**

Non-woven. No pattern repeat but product has directional grain. Product may vary from samples and batch to batch due to fiber blending and lay-up which is an inherent feature of this product.

#### **ENVIRONMENTAL**


Autex is committed to best practice through our ISO 9001 and ISO 14001 certified Quality and Environmental Management Systems.

Autex Composition contains a minimum of 60% previously recycled polyester fiber (from PET bottle-flake). Off-cuts and manufacturing waste are re-used or recycled wherever possible.

Autex Composition is manufactured from 100% polyester fibers and does not contain formaldehyde binders. Autex polyester fibers support safer indoor air quality and will not become a potential airborne pollutant.

#### **SERVICE**

For further information about Composition or any other Autex product, please contact your Autex account manager or visit our website.





## **COMPOSITION**® COLOR OPTIONS





To order a color sample, please contact your Autex account manager or visit www.autexindustries.com

## COMPOSITION® COLOR OPTIONS



To order a color sample, please contact your Autex account manager or visit www.autexindustries.com





# CARING FOR THE ENVIRONMENT

Autex products are manufactured using 100% polyester fiber and aim to contain a minimum of 60% previously recycled fiber (from PET plastics). They are designed to be recycled at the end of their life too. We use Life Cycle Analysis (LCA) to understand the environmental impacts of our products and set targets to reduce these. All our products have been verified as low VOC and are free from harmful chemical binders making them great for indoor environmental quality (IEQ).

We have continual improvement programmes in which we implement a range of initiatives to mitigate the environmental 'hotspots' that we have identified. Our products are GreenRate Level A and LCARate Gold certified.

Composition® is also Declares certified to be Red List free and can be used in Living Building Challenge projects. Autex has a high functioning Environmental Management System (ISO 14001) to enhance its environmental performance and contribute to sustainable development.









14

Autex Industries Ltd

702-718 Rosebank Rd, Private Bag 19988, Avondale 1746, Auckland, New Zealand Freephone 0800 428 839 Phone +64 9 828 9179 Fax +64 9 828 5810

www.autex.co.nz

Autex Australia Pty Ltd

166 Bamfield Road, 166 Bamhteld Road,
PO Box 5099,
West Heidelberg, Melbourne,
VIC 3081, Australia
Freephone 1800 678 160
Phone +61 3 9457 6700
Fax +61 3 9457 1020

www.autex.com.au

Autex Acoustics Ltd

Unit J4, Lowfields Way, Lowfields Business Park, Elland, West Yorkshire, Hx5 9Da, United Kingdom
Phone +44 (0) 1422 418899

www.autexacoustics.co.uk

Autex Acoustics LLC 19350 Van Ness Avenue Torrance, CA 90501

United States of America Phone **+1(310)490-1591** 

www.autexacoustics.com

**Autex Acoustics** Asia Sdn. Bhd

03-05, Indah Walk 3, Jalan Indah 15, Taman Bukit Indah, 79100, Iskandar Puteri,

www.autexacoustics.asia